

## Product Data Sheet

Product name: 2lbs Minicell foam

### Description:

- Closed cell PE crosslinked polyolefin foam in bun (block) form
- Multiple colors available
- Meets the requirements of FMVSS 302 at 0.250" (1/4") (6.35mm) and higher

### Typical Physical Properties

Property		Test Method	Unit	Value
Cell Structure		-	-	Closed
Color		-	-	Multiple
Compression Deflection 25%		ASTM D 3575 Suffix D	psi kPa	4 - 10 28 - 69
Compression Set (Room temp)		ASTM D 3575 Suffix B	%	30 max
Density		ASTM D 3575 Suffix W	lb/ft <sup>3</sup> kg/m <sup>3</sup>	1.5 - 2.5 25 - 40
Elongation		ASTM D 3575 Suffix T	%	100 min
Flammability		FMVSS 302	in mm	0.25 and higher 6.35 and higher
Service Temperature	Low	-	°F °C	-65 -54
	High Intermittent	-	°F °C	210 99
Tear Strength		ASTM D 3575 Suffix T	lb/in kN/m	6.86 min 1.2 min
Tensile Strength		ASTM D 3575 Suffix T	psi kPa	26.1 min 180 min
Thermal Stability		ASTM D 3575 Suffix S	%	5 max
Water Absorption		ASTM D 3575 Suffix L	lb/ft <sup>2</sup> kg/m <sup>2</sup>	0.1 max 0.5 max
Shore Hardness 00		ASTM D2240	-	50

**\*\* This product is not intended for elevated temperature applications. \*\***

All data and technical information are based on results achieved under the specific conditions defined according to the testing standards referenced. The products discussed are sold without representation or warranty, either expressed or implied. Foam N' More shall not be liable for any loss or damage resulting from inappropriate usage. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. Specifications may be changed at the discretion of Foam N' More without prior notification.